

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
4 December 2003 (04.12.2003)

PCT

(10) International Publication Number  
**WO 03/100336 A1**

(51) International Patent Classification<sup>7</sup>: **F27D 21/00, 1/16**

26, 44287 Dortmund (DE). **LAMM, Rolf**; Graf-Schwerin-Strasse 44, 52066 Aachen (DE).

(21) International Application Number: **PCT/EP03/05332**

(22) International Filing Date: **21 May 2003 (21.05.2003)**

(74) Agents: **BERND, Janssen et al.**; Uexküll & Stolberg, Beselerstr. 4, 22607 Hamburg (DE).

(25) Filing Language: **English**

(81) Designated States (*national*): AU, BR, CA, CN, HU, ID, IL, IN, JP, KP, MX, NO, NZ, PL, RU, UA, ZA.

(26) Publication Language: **English**

(30) Priority Data:  
102 23 284      24 May 2002 (24.05.2002)      DE

(84) Designated States (*regional*): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).


(71) Applicant: **SPECIALTY MINERALS MICHIGAN INC.** [US/US]; 30600 Telegraph Road, Bingham Farms, MI 48025 (US).

Published:  
— with international search report

(72) Inventors: **BLISSENBACH, Dieter**; Bernsberger Str. 44, 47445 Moers (DE). **KIRCHHOFF, Stefan**; Exzellenzstr.

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: **A METHOD FOR REPAIRING A PROTECTIVE LINING OF AN INDUSTRIAL REACTION OR TRANSPORT VESSEL**



(57) Abstract: The present invention relates to a method for repairing a protective lining of an industrial reaction or transport vessel, such as a converter vessel, electric arc furnace, or ladle. The method comprises identifying combined areas of the lining having a thickness below a predetermined threshold value by means of a measuring device, which measuring device measures the residual thickness of the lining and a processing unit, which processing unit in a first step transforms the residual thickness data into binary data, by comparing the measured residual thickness data with the pre-determined threshold value for the thickness of the lining, and assigning the binary value "1" to areas of the lining having a thickness below the pre-determined threshold value, and the binary value "0" to areas of the lining having a thickness equal or higher than the pre-determined threshold value, or vice versa, in a second step combines isolated areas of the lining having a thickness below the predetermined threshold value into combined areas of the lining to which the binary value for areas of the lining having a thickness below the pre-determined threshold value is assigned, and in a third step computes the position and repair sequence of each of the combined areas and transfers these data to a repair device, and applying monolithic lining material onto the combined areas computed by the processing unit by means of a repair device.

WO 03/100336 A1

## **A method for repairing a protective lining of an industrial reaction or transport vessel**

### **Background of Invention**

The present invention relates to a method for repairing a protective lining of an industrial reaction or transport vessel, such as a converter vessel, electric arc furnace, or ladle, e.g. steel casting ladle, pig iron ladle, torpedo ladle or slag ladle. In particular, the present invention relates to a method for repairing a protective lining of an industrial reaction or transport vessel, wherein areas of the lining having a thickness below a pre-determined threshold value are identified and monolithic lining material is applied onto those areas.

Industrial reaction or transport vessels, such as blast furnaces, electric arc furnaces, ladles or converters, are e.g. used for metallurgical purposes such as for producing steel. These vessels generally have a protective lining at their inner surface, which protects the outer metallic surface of the vessel from being damaged by the heat or reaction conditions inside the vessel. However, the protective lining is subjected to wear during the use of the vessels and must be repaired from time to time to ensure high operational safety.

For this purpose, the residual thickness of the protective lining is measured between the individual phases of use of the vessel, when the vessel is empty. The residual thickness

data obtained by this measurement are used to determine the areas of the lining which have to be repaired.

International Patent Application WO 01/38900 A1 discloses a non-contacting measuring procedure for measuring the residual thickness of the refractory lining of a metallurgical vessel. The method comprises sweeping a laser beam from a measuring device over the inner surface of the metallurgical vessel, i.e. the surface of the refractory lining, and measuring the angle and the distance between measuring device and inner surface of the vessel at various points. The measuring device preferably includes a laser diode operating in a pulse mode as a transmitting device and a photodiode as a receiving device. The thus obtained data allow to image the surface structure of the refractory lining in the form of a three-dimensional thickness profile. WO 01/38900 A1 suggests that the measuring device is physically associated with a device which applies new lining material to the inside surface of the vessel.

However, the lining material is generally applied manually to the inside surface of the vessel, either by means of an operator holding a repair device or by means of a repair device which is manually manipulated by an operator via a remote. In both cases the operator must be able to visibly identify the areas to be repaired and follow the movements of the repair device. Therefore, the operator has to be relatively close to the open-end of the vessel to be repaired. This is connected with several drawbacks. The operator is exposed to heat, fire, rebound of new lining material and other parts falling off the vessel. Furthermore, there is the danger of explosion in the vessels, if the hot material gets into contact with water, which may cause harm to the operator, if the operator is close to the vessel.

Moreover, the manual method is inherently connected with human errors. For instance, if the operator misses the right spot to be repaired, e.g. by a few centimeters, there is the danger of causing a so called "breakthrough", which is a hole in the wall of the vessel, and may harm the operator of the vessel or damage the equipment connected with the vessel or even lead to explosions if the material flowing out of the vessel comes in contact with water. This may be a problem because it is difficult to visibly identify the areas to be repaired if the protective lining is entirely monolithic, and the operator can only obtain a rough guidance by the measurement of the thickness profile carried out before.

If the operator actually holds the repair device, the output of new lining material is generally limited. Furthermore, because of the heat, repair time under control of an operator is generally limited to 10 to 15 minutes.

Accordingly it would be highly desirable to provide a method for repairing a refractory lining of a metallurgical vessel which is more accurate than the methods according to the

state of the art, using less material and which eliminates the operational dangers mentioned before.

#### Summary of Invention

It is an object of the present invention to provide a method for repairing a monolithic lining of an industrial reaction or transport vessel which can be performed automatically, at high speed and high accuracy.

It is another object of the present invention to provide a method for repairing a monolithic lining of an industrial reaction or transport vessel where the operational dangers are eliminated.

It is a further object of the present invention to provide a method for repairing a monolithic lining of an industrial reaction or transport vessel which uses lining material more effectively.

It is a still further object of the present invention to provide a method for repairing a monolithic lining of an industrial reaction or transport vessel which is easily adaptable to operational requirements.

In its broadest aspect, the present invention provides a method for repairing a protective lining of an industrial reaction or transport vessel including the steps of

identifying combined areas of the lining having a thickness below a pre-determined threshold value by means of a measuring device, which measuring device measures the residual thickness of the lining and a processing unit, which processing unit in a first step transforms the residual thickness data into binary data, by comparing the measured residual thickness data with the pre-determined threshold value for the thickness of the lining, and assigning the binary value "1" to areas of the lining having a thickness below the pre-determined threshold value, and the binary value "0" to areas of the lining having a thickness equal or higher than the pre-determined threshold value, or vice versa, in a second step combines isolated areas of the lining having a thickness below the pre-determined threshold value into combined areas of the lining to which the binary value for areas of the lining having a thickness below the pre-determined threshold value is assigned, and in a third step computes the position and repair sequence of each of the combined areas and transfers these data to a repair device,

and applying monolithic lining material onto the combined areas computed by the processing unit by means of a repair device.

### Detailed Description of the Invention

For actual performance of the repair, a repair device is provided which applies new lining material onto the damaged areas of the lining and which preferably includes a manipulator arm and a gunning nozzle which is disposed thereon and is rotatable, tiltable, vertically movable, and optionally horizontally movable. The position and operation of the repair device is controlled by a processing unit which transfers the actual residual thickness data obtained by means of the measuring device to the repair device in the form of repairing instructions. The processing unit is preferably electronically connected with both, the measuring device and the repair device.

The present method includes number of processing steps for transferring the actual residual thickness data obtained by means of the measuring device to the repair device in the form of repair instructions. The residual thickness data are preferably sorted with reference to a regular grid which reflects the symmetry of the vessel. Since the preferred metallurgical vessels have a basic shape which substantially is in the form of a cylinder the residual thickness data are preferably converted into matrices and cylinder coordinates. If the vessel has a rectangular horizontal cross section, the residual thickness data are preferably converted into matrices and cartesian coordinates.

The processing steps include transforming the residual thickness data into binary data, by comparing the residual thickness data with the pre-determined threshold value for the thickness of the lining, and e.g. assigning the binary value "1" to areas of the lining having a thickness below the pre-determined threshold value, and the binary value "0" to areas of the lining having a thickness equal or higher than the pre-determined threshold value, hereinafter referred to as "binarization".

To reduce the amount of data to be processed, before binarization, the three-dimensional residual-thickness data obtained by the measuring device of a number of points in the vessel may preferably be averaged in the processing unit, in a first processing step referred to as "averaging".

After binarization, isolated areas of the lining having a thickness below the pre-determined threshold value are combined into adjacent combined areas of the lining to which the binary value for areas of the lining having a thickness below the pre-determined threshold value is assigned, which processing step is hereinafter referred to as "defragmentation". For achieving this, the binary values of a number of areas are preferably compared with each other, and, if the number of areas of the lining having a thickness below the pre-determined threshold value exceeds a pre-selected ratio, the whole compared area is assigned the binary value for areas having a thickness below the pre-determined threshold value. Thereby

the fact is accepted that areas of the lining having a thickness equal or higher than the pre-determined threshold value adjacent to areas of the lining having a thickness below the pre-determined threshold value will be sprayed on with new lining material as well, although these areas do not require a repair yet. A preferred ratio is e.g. from about 30 per cent to about 80 per cent, most preferably from about 50 per cent to about 60 per cent.

The defragmentation can be carried out using different degrees of defragmentation. Preferably, the degree of defragmentation is varied as a function of the production-related boundary conditions such as the uniformity in reconstituting the refractory lining, mass of the relining compound, and time of repair.

Finally, the position and repair sequence of each of the combined areas is computed and converted into repair instructions for the repair device in a further processing step. Therefore, each computed area having the binary value for areas having a thickness below the pre-determined threshold value is associated with a consecutive number representing the sequence of steps of application of monolithic lining material. This processing step is hereinafter referred to as "sequencing". The sequence is preferably selected, taking into account the static characteristics and the curing behavior of the repair material that is applied onto the inner surface of the monolithic lining, in particular the curing time of the repair material. In particular, the preferred sequence takes into account that the refractory lining has to be repaired from the lower sections of the metallurgical vessel to its upper sections. Thereby the repair material, if applied in form of horizontal strips to the repair areas, is supported by the relining compound applied in adjacent lower sections before.

In a particularly preferred aspect of the invention, the residual-thickness data are processed to obtain repair data in such a way that the shape of each area to be repaired, as seen towards the surface of the refractory lining, is enlarged into a simple geometrical basic shape, preferably a rectangle. Thereby the working speed of the repair device may be further increased.

In a further particularly preferred aspect of the invention, the orientation and form of the geometrical basic shape is adapted, in the processing unit, to the existing axes of motion of the repair device, which is preferably a spraying, a gunning or a shotcreting device and the like. With this adaptation the repair device can be moved along its existing axes of motion in order to perform the repair of the refractory lining. Thereby the working speed of the repair device is increased and the repair device is easier to control. This processing step is preferably carried out after defragmentation, and is hereinafter referred to as "segmentation".

In a further preferred aspect of the present invention, prior to determining the sequence of steps of application of monolithic lining material, the steps of binarization,

defragmentation, and optionally segmentation are carried out again under variation of the threshold value, so that deeper holes may be repaired in multiple repair steps by applying a multiplicity of layers of monolithic lining material.

In a still further, particularly preferred aspect, prior to a transfer of the repair data to the repair device, the result of the repair is represented in the processing unit by means of a simulation under consideration of specific operational parameters such as the time of repair, and amount of the repair compound. Thus, the operator of the processing unit may easily adapt the repair procedure to varying conditions.

It is particularly preferred that, after completion of the spraying step, the residual thickness of the refractory lining is once again measured by the measuring device and the thus obtained residual thickness data are compared with data obtained by a simulation regarding the achievable reconstitution of the refractory lining, and in case of a deviation between the newly measured residual thickness data and the simulation data, the control unit of the repair device is calibrated accordingly. Alternatively, a further repair step may be started.

The invention will be exemplary described below in more detail with reference to the attached figures, wherein

Fig. 1 shows a schematic view of a metallurgical vessel formed as an electric arc furnace, a measuring device for wear determination and a gunning device for repairing the refractory lining,

Fig. 2 shows a cut-out of the binarized matrix reflecting the refractory lining of an electric arc furnace,

Fig. 3 shows a cut-out of the defragmented matrix of the refractory lining of an electric arc furnace,

Fig. 4 shows a cut-out of the segmented matrix of the refractory lining of an electric arc furnace, and

Fig. 5 shows a cut-out of the sequenced matrix of the refractory lining of an electric arc furnace.

In particular, Figure 1 shows a schematic view of a metallurgical vessel 1 formed as an arc furnace with a refractory lining 2 which requires a repair. A repair device 3 is provided for the repair of the lining 2 and is formed as a gunning device having a gunning head 4 and a manipulator 5. The gunning device pneumatically conveys a dry refractory mix through a nozzle 4b of the gunning head 4 and at the nozzle 4b water will be added to the refractory mix. It is also possible that the repair device is a shotcreting device. In contrast to the afore-

mentioned gunning device the shotcreting device conveys a wet refractory mix through the shotcreting head with air and a reactive compound added to the wet refractory mix at the nozzle 4b. Manipulator 5 substantially includes a stationary column 5a rotatable about a vertical axis to the upper end of which an angular extension arm 5b is hinged. Gunning head 4 is suspended at the end of angular extension arm 5b facing away from column 5a. Extension arm 5b is pivotally supported about a horizontal axis at the upper end of column 5a. Gunning head 4 is pivotally supported about another axis which is substantially vertical and runs in parallel with the column 5a. Furthermore, gunning head 4 has a gunning arm 4a with a nozzle 4b that is pivotally mounted on gunning head 4. Thus, repair device 3 has four rotatory freedom degrees to allow a travel to the individual areas requiring a repair within metallurgical vessel 1. Drives (not shown) which are triggered via a control unit 6 for the repair procedure are provided to carry out the single rotational and pivotal motions of repair device 3. The control data referred to as repair data to perform the repair procedure are received by control unit 6 from a processing unit 7 which evaluates and processes relevant information from a measuring device 8. Measuring device 8 serves for determining the wear of refractory lining 2 and substantially includes a laser working in a non-contacting manner. For the measuring procedure measuring device 8, disposed at a free-end of a carrier arm 9, is moved over the opening 10 of the hot metallurgical vessel 1.

The residual thickness data determined by measuring device 8 are transferred from measuring device 8 to a processing unit 7. The processing unit 7 carries out the steps described herein before to process the residual thickness data received from the measuring device 8 into repair instructions for the repair device 3.

In Figure 2, a binarized matrix is shown by way of example, the binarized matrix covers the depth range T of from 2 m to 3.6 m and the full angle range w (from 0° to 360°). The logical value "1", corresponding to areas which require repair, is represented in form of black areas and the logical value "0", corresponding to areas which do not require repair, is represented in form of white areas.

An example of a defragmented matrix of the identical cut-out is shown in Figure 3. This matrix has been created by comparing the binary values of a number of areas within a larger square section and determining whether the number of black areas within that section exceeds a ratio of 60 per cent. If the number exceeded the ratio of 60 per cent, then the whole area was assigned the binary value "1"; if the number did not exceed the ratio of 60 per cent, then the whole area was assigned the binary value "0". This procedure has been applied throughout the entire binarized matrix, and has been repeated 6 times, each time with increasing size of the enlarged sections.



Figure 4 illustrates the same matrix in a segmented form. The segment borderings are shown as lines around the fields having the binary value "1". The method employed for segmentation analyzed a multiplicity of adjacent series of fields in the defragmented matrix. If an adjacent series of fields having the binary value "1" has been found in the actually traversed line, the borderings thereof were determined. The so identified area was transformed to a regular rectangle and assigned a consecutive number.

Figure 5 illustrates the sequence of the repair procedure, starting from area assigned consecutive number 1. The sequence has been determined under consideration that vertically adjacent areas are repaired from bottom to top, and that the whole distance to be travelled by the manipulator is minimal.

Claims

1. A method for repairing a protective lining of an industrial reaction or transport vessel including the steps of identifying combined areas of the lining having a thickness below a pre-determined threshold value by means of a measuring device, which measuring device measures the residual thickness of the lining and a processing unit, which processing unit in a first step transforms the residual thickness data into binary data, by comparing the measured residual thickness data with the pre-determined threshold value for the thickness of the lining, and assigning the binary value "1" to areas of the lining having a thickness below the pre-determined threshold value, and the binary value "0" to areas of the lining having a thickness equal or higher than the pre-determined threshold value, or vice versa, in a second step combines isolated areas of the lining having a thickness below the pre-determined threshold value into combined areas of the lining to which the binary value for areas of the lining having a thickness below the pre-determined threshold value is assigned, and in a third step computes the position and repair sequence of each of the combined areas and transfers these data to a repair device, and applying monolithic lining material onto the combined areas computed by the processing unit by means of a repair device.
2. The method of claim 1, wherein the protective lining is a refractory lining.
3. The method of any one claims 1 or 2, wherein the industrial reaction or transport vessel is a metallurgical vessel.
4. The method of claim 3, wherein the metallurgical vessel is selected from a converter vessel, an electric arc furnace, a blast furnace, a ladle, a tundish and a coke oven chamber.
5. The method of claim 4, wherein the ladle is selected from a steel casting ladle, pig iron ladle, torpedo ladle and slag ladle.
6. The method of any one of the preceding claims, wherein the measuring device is a laser-based measuring device.
7. The method of claim 6, wherein the laser-based measuring device is a mirror scanner.

8. The method of any one of the preceding claims, wherein the repair device comprises a manipulator arm and a gunning nozzle which is disposed thereon and is rotatable, tiltable and vertically movable.
9. The method of any one of the preceding claims, wherein the repair device is selected from a spraying, a gunning and a shotcreting device.
10. The method of any one of the preceding claims, wherein the processing unit is electronically connected with the measuring device and the repair device.
11. The method of any one of the preceding claims, wherein steps within the processing unit are carried out electronically.
12. The method of any one of the preceding claims, wherein the processing unit combines the isolated spots into rectangular combined areas.
13. The method of any one of the preceding claims, wherein the position of each of the combined areas are computed in the form of cylinder coordinates.
14. The method of any one of the preceding claims, wherein the residual thickness of the refractory lining is once again measured by the measuring device, after completion of the repair step and the thus obtained residual thickness data are compared with data obtained by a simulation regarding the achievable reconstitution of the refractory lining, and in case of a deviation between the newly measured residual thickness data and the simulation data, the control unit of the repair device is calibrated accordingly.
15. The method of any one of the preceding claims, wherein the residual thickness of the refractory lining is once again measured by the measuring device, after completion of the repair step and the thus obtained residual thickness data are compared with data obtained by a simulation regarding the achievable reconstitution of the refractory lining, and in case of a deviation between the newly measured residual thickness data and the simulation data, the processing and repair sequence is repeated.




Fig. 1

WO 03/100336

PCT/EP03/05332

T

2/3




Fig. 2

T




Fig. 3

WO 03/100336

PCT/EP03/05332

3/3




Fig. 4




Fig. 5

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 03/05332

A. CLASSIFICATION OF SUBJECT MATTER  
 IPC 7 F27D21/00 F27D1/16

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 F27D C21C B22D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 107 244 A (OCHIAI TSUNEMI ET AL) 15 August 1978 (1978-08-15) claims 1,6-10 column 4, line 7 - line 68 column 5, line 17 - line 26 column 6, line 62 - column 7, line 26 column 8, line 66 - column 9, line 2	1-15
P,X	US 2002/158368 A1 (WIRTH EMIL J) 31 October 2002 (2002-10-31) paragraphs '0044!-'0049!; claims 3,9-12	1-13
A	US 4 649 858 A (NARITA YUJI ET AL) 17 March 1987 (1987-03-17) column 4, line 9 - line 50; claim 1 -/-	1-15

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

11 August 2003

Date of mailing of the international search report

26/08/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax: (+31-70) 340-3016

Authorized officer

González-Junquera, J

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 03/05332

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 212 738 A (CHANDE ALHAD M ET AL) 18 May 1993 (1993-05-18) claims 1-20	1-15



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 03/05332

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4107244	A	15-08-1978	JP 1227178 C	31-08-1984
			JP 51147510 A	17-12-1976
			JP 55005038 B	02-02-1980
			AU 498518 B2	15-03-1979
			AU 1489276 A	22-12-1977
			DE 2626421 A1	16-12-1976
			FR 2314531 A1	07-01-1977
			GB 1539051 A	24-01-1979
			IT 1063328 B	11-02-1985
US 2002158368	A1	31-10-2002	WO 02087819 A1	07-11-2002
US 4649858	A	17-03-1987	JP 1877940 C	07-10-1994
			JP 6005155 B	19-01-1994
			JP 61093384 A	12-05-1986
			AU 566699 B2	29-10-1987
			AU 4843985 A	17-04-1986
			DE 3536113 A1	24-04-1986
			FR 2571835 A1	18-04-1986
			ZA 8507820 A	28-05-1986
US 5212738	A	18-05-1993	AU 1760492 A	17-11-1992
			CA 2105862 A1	13-10-1992
			EP 0579746 A1	26-01-1994
			MX 9201608 A1	01-10-1992
			WO 9218829 A1	29-10-1992